



KROXX W-100

TECHNICAL

1. PRODUCT DESCRIPTION

Kroxx W-100 bonds to wide variety of materials including wood, paper, cardboard, leather, fabrics, etc. Bond times vary according to the substrates being bonded but are generally faster than normal superglues.

2. TYPICAL APPLICATIONS

Typical applications included wood trim on furniture, balsa wood bonding, thread termination on book bindings. Recommended for use on porous materials or relatively smooth even surfaces.

3. PROPERTIES OF UNCURED MATERIAL

Resin	Ethyl Cyanoacrylate
Appearance	Clear Liquid
Viscosity	80 ~ 110cps
Flash Point	> 85°C
Shelf Life	12months at 25°C
Max. OperatingTemp.	-20°C to 80°C
Typical Cure Speed	Hemlock/Hemlock <15sec
	Beech / Beech <20sec
	Cyprus / Cyprus <20sec
	Oak / Oak <30sec
Leather / Leather <20sec	
Full Cure Time	24hours at 20°C
Tensile Shear Strength	min. 100kgf / cm ²

4. DIRECTIONS FOR USE

Bond speed is very fast so ensure that parts are properly aligned before bonding. Activators may be required if there are gaps or porous surfaces. Some plastics may require Primer. Ensure parts are clean, dry and free from oil and grease. Product is normally hand applied from the bottle. Apply sparingly to one-surface and press parts firmly together until handling strength is achieved. As a general rule, as little cyanoacrylate as possible should be used – over application will result in slow cure speed and lower bond strength

5. STORAGE

Store in a cool area out of direct sunlight. Refrigeration to 5° C gives optimum storage stability.

6. CURE SPEED VS. BOND GAP

Kroxx superglues give best results on close fitting parts. The product should be applied in a very thin line in order to ensure rapid polymerisation and a strong bond. Excessive bond gaps will result in slower cure speeds. Cyanoacrylate Activators may be used to greatly increase cure speeds

7. CURE SPEED VS. ENVIRONMENTAL CONDITIONS

Kroxx superglues require surface moisture on the substrates in order to initiate the curing mechanism. The speed of cure is reduced in low- humidity conditions. Low temperatures will also reduce cure speed. All figures relating to cure speed are tested at 21°C.

8. TYPICAL ENVIRONMENTAL RESISTANCE

Hot strength

Kroxx superglues are suitable for use at temperatures up to 80°C. At 80°C the bond will be approximately 70% of the strength at 21°C. The bond strength at 100°C is approximately 50% of full strength at 21°C.

Heat ageing

Kroxx superglues retain over 90% of their strength when heated to 80°C for 90 days and then tested at 21°C. Heating the bond to 100°C and then testing at 21°C gives bond strength of approximately 50% of initial strength.

Chemical / Solvent Resistance

Kroxx superglues exhibit excellent chemical resistance to most oils and solvents including motor oil, leaded petrol, ethanol, propanol and freon. Cyanoacrylates are not resistant to high levels of moisture or humidity over time.

9. DATA RANGES

The data contained in this data sheet may be reported as typical value and/or range. Values are based on actual test data and are verified on a regular basis.

NOTES

The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Kroxx Inc. and its agents cannot assume liability or responsibility for results obtained in the use of its product by persons whose methods are outside or beyond our control. It is the user's responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the user's responsibility to observe and adapt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.

PLEASE CONTACT KROXX INC. FOR ASSISTANCE AND RECOMMENDATIONS

Kroxx Inc. 526-6 Deungchondong, Kangsogu, Seoul, Kroea

Tel: 82-2-2652-1311 Fax: 82-2-2652-2117

Web: www.kroxx.com